

CHERAN SPINNER PRIVATE LIMITED
TECHNICAL SPECIFICATION

DATE:30.06.2022

1	COUNT	Ne 40/1
2	MATERIAL & BLEND	TENCEL-100%
4	ACTUAL COUNT Ne	40
5	C.S.P *	4500
6	COUNT CV	1.5
7	STRENGTH CV	4.5
8	T.P.I / T.P.M	22.80 / 897
9	R.K.M * (TENSOMAXX)	26
10	R.K.M CV	9%
11	ELONGATION	7.5
12	ELONGATION CV	9.50%
13	HAIRINESS **	5.5
14	IMPERFECTION (UT 4)	
	U%	10.5
	THIN (- 50%) / KM	4
	THICK (+ 50%) / KM	16
	NEPS (+ 200%) / KM	50
	TOTAL	70

AUTO CONED / SPLICED

**

HAIRINESS (H) Tested in UT 4 SE.


