

**SRI KUMARAN SYNTHETICS INDIA (P) Ltd.,
SPECIFICATION OF 40S PC (65/35) COUNT**

COUNT	40' PC (65/35)
Avg. Count	40.94
Avg. Strength	90.30
CSP	3697
CT-CV%	1.03
Strg-CV%	3.91
U%	10.71
THIN -30%	1365
THIN -40%	108
THIN -50%	2
THICK -35%	426
THICK -50%	82
NEPS -140%	591
NEPS -200%	192
Total Imp Norm	282
Total Imp Extra	1125
HAIR	4.7
SH	1.11

TENSO JET(UTJ4)

	23.97
TENACITY - Mean	7.80
TENACITY - CV%	6.94
Elong-Mean	5.53
Elong-CV%	
CMT - 3	222
Total CMT	1
OBJ.FAULTS(7CLASS)	3
SERIOUS FAULTS (A3,B3,C2,D2)	1
LONG THICK (E,F,G)	11
LONG THIN (H1,H2,I1,I2)	